

ARBOFORM® ZE 50 natur

Cellulose Acetate

TECNARO GmbH

Описание материалов:

Thermoplastics from renewable resources for plastics processing

Our granules ARBOFORM ® , ARBOBLEND ® and ARBOFILL ® can be processed with injection moulding, extrusion, calendering, blow molding, deep drawing or pressing into moulded parts, half-finished product, sheets, films oder profiles.

ARBOFORM® is the ecological, aesthetic and yet sophisticated alternative to your plastics products.

ARBOFORM® offers plastics-specific processing capability which means competitive pricing and high accuracy for products so far machined from laminated wood, presspahn or MDF board. What is more, ARBOFORM® is clean by ecological standards, ensuring more environmentally sound manufacture and disposal than the above wood materials that use toxic glue binders.

As against expensive solid wood shapes, which, besides, are often made from Tropical woods, it is the fact that it can be freely and accurately formed that lets ARBOFORM® compare favourably with conventional, mostly rather plain wood shapes. Apart from providing a pleasing natural surface, inexpensive refinement by adding real wood veneers, or even three-dimensional inlay work at moderate pricing is possible for most applications.

Главная Информация			
Характеристики	Биоразлагаемый Низкий и без запаха Содержание возобновляемых ресурсов		
Используется	Электрическое/электронное применение Ювелирные изделия Игрушки		
Внешний вид	Натуральный цвет		
Формы	Гранулы		
Метод обработки	Выдувное формование Каландрирование Экструзия Литье под давлением Пресс-форма		
Механические	Номинальное значение	Единица измерения	Метод испытания
Модуль растяжения	4850	МПа	ISO 527-2
Tensile Stress			ISO 527-2
Yield	29.2	МПа	
Break	29.2	МПа	
Растяжимое напряжение			ISO 527-2
Yield	0.69	%	
Break	0.69	%	
Воздействие	Номинальное значение	Единица измерения	Метод испытания

Ударная прочность

5.0

kJ/m²

ISO 179

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай



WeChat