

Tecnoflon® FOR 9385F

Fluoroelastomer

Solvay Specialty Polymers

Описание материалов:

TECNOFLON® FOR 9385F is a medium viscosity cure incorporated fluoroelastomer terpolymer (FKM) with 68.5 % fluorine content. Tecnoflon® FOR 9385F is designed to improve bonding in any application requiring adhesion to metal. In shaft seals or valve stem seals production, Tecnoflon® FOR 9385F greatly reduces the reject rate due to adhesion and molding problems.

Some of the basic properties of Tecnoflon® FOR 9385F are:

Superior bonding to metal

Very good scorch safety

Outstanding processability

Lack of mold fouling

Excellent hot tear resistance

Excellent mold release

Tecnoflon® FOR 9385F can be used for compression, injection and transfer molding of shaft seals, valve stem seals, O-rings, gaskets and seals. This material can be extruded into hoses or profiles and can be calendered to make sheet stocks or belting. Tecnoflon® FOR 9385F can be combined with the cure system and other typical fluoroelastomer compounding ingredients. Mixing can be accomplished with two-roll mills or internal mixers.

Главная Информация

Характеристики	Bondability
	Хорошая адгезия
	Хороший выпуск пресс-формы
	Хорошая технологичность
	Хорошая прочность на разрыв
	Средняя вязкость
	Терполимер
Используется	Ремни/ремонт ремней
	Смешивание
	Прокладки
	Шланг
	Профили
	Уплотнения
	Лист
Внешний вид	Кремowo-белый
	Плита
	Экструзия
Формы	Плита
Метод обработки	Каландрирование
	Уплотнение
	Прессформа сжатия
	Экструзия

Литье под давлением

Литье из смолы

Физический	Номинальное значение	Единица измерения
Вязкость Mooney ¹ (ML 1+10, 121°C)	45	MU
Содержание фтора ²	69	%

NOTE

- | | |
|----|-------------|
| 1. | Raw polymer |
| 2. | Raw polymer |

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай



WeChat